



www.suntexcomposite.com

TECHNICAL DATA SHEET

STYLE: GF200P-AC215-3001

DESCRIPTION

GF200P-AC215-3001 is a light weight fiberglass fabric, acrylic weaveset finish-medium add-on to improve fabric processing in sewing and laminating. It's used for insulation covers , hull board fabric and other types of fire control systems.

BASE FABRIC

Base fabric style No. GF200P

	<u>(Metric)</u>	<u>(English)</u>	<u>Test methods</u>
Weave	Plain	Plain	
Yarn			
Warp	EC9 68 1*0	ECG75 1/0	
Weft	EC9 68 1*0	ECG75 1/0	
Construction			
Warp	18 ± 0.5 ends /cm	46 ± 1 ends/inch	ASTM D 3775-96
Weft	12 ± 0.5 picks /cm	31 ± 1 picks/inch	ASTM D 3775-96
Weight	200 ± 10 g/m ²	5.92 ± 0.29 oz/yd ²	ASTM D3776-96
Thickness	0.18 ± 0.02 mm	0.007 ± 0.0007 inch	ASTM D1777-96

FINISHED FABRIC

Finishing style No. AC215-3001

Coating	Acrylic weave-set finish two sides, medium add-on, black color		
Weight	220 ± 10 g/m ²	7.06 ± 0.6 oz/yd ²	ASTM D3776-96
Thickness	0.20 ± 0.02 mm	0.007 ± 0.0007 inch	ASTM D1777-96
Color	Black		
Temp resistance	550 ⁰ C	1000 ⁰ F	

All data in this specification sheet are representative which we believe to be accurate, but is given without guarantee or responsibility on our part. Anyone intending to use recommendation herein should make their own assessment of the suitability for the purpose required.

SUNTEX COMPOSITE INDUSTRIAL CO., LTD.
1212 Fortune International Building, 717 Wuluo Road, Wuhan
CHINA 430072
Tel: +86-27-878 69 042
Fax: +86-27-871 64 892
Email: suntex@public.wh.hb.cn
info@suntexcomposite.com